

Tolerances on thickness (\pm mm) Figures in brackets () are outside the range of BSEN 60893 but apply if no customer specific tolerance.

Where the nominal thickness is not a preferred thickness, the tolerance for the next higher preferred nominal thickness applies.

| Nominal thickness | SRBP based | SRBF B10/B10s B11 | SRBF B12/B12s | SRBG based | SRBG Polyimide Glass | Epoxy Cotton |
|-------------------|------------|-------------------|---------------|------------|----------------------|--------------|
| 0,4 | 0.07 | 0.09 | - | 0,10 | - | - |
| 0,5 | 0.08 | 0.13 | - | 0,12 | - | - |
| 0,6 | 0.09 | 0.14 | - | 0,13 | - | - |
| 0,8 | 0.1 | 0.15 | 0.19 | 0,16 | 0.16 | 0.16 |
| 1,0 | 0.12 | 0.16 | 0.2 | 0,18 | 0.18 | 0.18 |
| 1,2 | 0.14 | 0.17 | 0.22 | 0,20 | 0.21 | 0.19 |
| 1,5 | 0.16 | 0.19 | 0.24 | 0,24 | 0.26 | 0.22 |
| 2,0 | 0.19 | 0.21 | 0.26 | 0,28 | 0.28 | 0.24 |
| 2,5 | 0.22 | 0.24 | 0.29 | 0,33 | 0.33 | 0.27 |
| 3,0 | 0.25 | 0.26 | 0.31 | 0,37 | 0.37 | 0.3 |
| 4,0 | 0.3 | 0.32 | 0.36 | 0,45 | 0.45 | 0.34 |
| 5,0 | 0.34 | 0.36 | 0.42 | 0,52 | 0.52 | 0.39 |
| 6,0 | 0.37 | 0.4 | 0.46 | 0,60 | 0.6 | 0.44 |
| 8,0 | 0.47 | 0.49 | 0.55 | 0,72 | 0.72 | 0.52 |
| 10,0 | 0.55 | 0.56 | 0.63 | 0,82 | 0.82 | 0.6 |
| 12,0 | 0.62 | 0.64 | 0.7 | 0,94 | 0.94 | 0.68 |
| 14,0 | 0.69 | 0.7 | 0.78 | 1,02 | 1.02 | 0.74 |
| 16,0 | 0.75 | 0.76 | 0.85 | 1,12 | 1.12 | 0.8 |
| 20,0 | 0.86 | 0.87 | 0.95 | 1,30 | 1.3 | 0.93 |
| 25,0 | 1 | 1.02 | 1.1 | 1,50 | 1.5 | 1.08 |
| 30,0 | 1.15 | 1.12 | 1.22 | 1,70 | 1.7 | 1.22 |
| 35,0 | 1.25 | 1.24 | 1.34 | 1,95 | (1.95) | 1.34 |
| 40,0 | 1.35 | 1.35 | 1.45 | 2,10 | (2.1) | 1.47 |
| 45,0 | 1.45 | 1.45 | 1.55 | 2,30 | (3.3) | 1.6 |
| 50,0 | 1.55 | 1.55 | 1.65 | 2,45 | (3.45) | 1.74 |
| 60,0 | - | (1.63) | (2.42) | - | - | (2.02) |
| 70,0 | - | (1.83) | (2.8) | - | - | (2.32) |
| 80,0 | - | (2.03) | (3.3) | - | - | (2.62) |
| 90,0 | - | (2.23) | (3.6) | - | - | (2.93) |
| 100,0 | - | (2.43) | (4.0) | - | - | (3.22) |