

**Date Generated: Monday 22nd of June 2026**

## **B42 Product Data Sheet**

# **BSEN60893-3-2-EPCC301 B42 Epoxy Cotton Laminate SRBF**

### **Material Details**

<b>Grade:</b>	B42
<b>Description:</b>	Epoxy Cotton. Anti-tracking, easy to machine
<b>Comments:</b>	Fine weave cotton epoxy laminate. Can be easily machined to a fine finish with good anti track properties, coupled with high mechanical and electrical strength.
<b>Specifications:</b>	BSEN60893-3-2-EPCC301 (Which supersedes BS2572 F6).
<b>Body Colour:</b>	Cream
<b>Cover Colour:</b>	Cream
<b>Finish:</b>	Satin/Glossy
<b>Size:</b>	1220 x 1220 Thickness Range: 0.8 - 150.0

### **Typical Applications**

- Busbar Supports
- Chemical Resistance Components
- Gears - Fine Tooth
- Gears - Medium Tooth
- High Voltage Insulation
- Precision Machined Parts
- Rotor Blades (compressor)
- Seal Rings
- Slot Wedges
- Track Resistance

### **General Properties**

Property	Unit of measure	Typical Value
Density	g/cm <sup>3</sup>	1.35
Water Absorption	mg	55

¥ Where relevant, the flammability test method is used solely to control and monitor consistency of production. Under no conditions should the results be considered in relation to fire hazards under actual conditions of use.

## Electrical Properties

Property	Unit of measure	Typical Value
IR (24hrs Water Immersed)	G Ω	6
IR (Dry)	G Ω	6
Electric Strength (Flat Rapid)	kV/mm	15
Breakdown Voltage (Edge Step by Step)	kV	70
Tracking Index	V	>600

## Mechanical Properties

Property	Unit of measure	Typical Value
Flexural Strength	MPa	190
Tensile Strength	MPa	80
Impact (Notched CHARPY)	kJ/m <sup>2</sup>	9.2

## Thermal Properties

Property	Unit of measure	Typical Value
Thermal Rating Continuous	°C	130
Thermal Rating Intermittent	°C	145

Disclaimer: The above values are based upon routine test data and do not form the basis of a supply contract. These products may be used in a diverse range of applications and whilst every effort is made to ensure the

information in this data sheet is accurate, it must be stressed that it is the user's responsibility to ensure suitability for the intended end use.

Source: <https://www.attwater.com/products/b42/>