

**Date Generated: Monday 15th of June 2026**

## **B4B Product Data Sheet**

# **BSEN60893-3-4-PFCP201 B4B Phenolic Paper Black Laminate**

### **Material Details**

<b>Grade:</b>	B4B
<b>Description:</b>	Phenolic Paper. Black Body and Cover
<b>Comments:</b>	<p>A high quality commercial grade for normal temperature and low-tension electrical applications.</p> <p>Similar to B4 with black core and covers.</p>
<b>Specifications:</b>	BSEN60893-3-4-PFCP201 (Which supersedes BS2572 P1). The closest NEMA equivalent to this specification is NEMA X
<b>Body Colour:</b>	Black
<b>Cover Colour:</b>	Black
<b>Finish:</b>	Satin/Glossy
<b>Size:</b>	<p>1220 x 1220</p> <p>Thickness Range: 0.8 - 75.0</p>

### **Typical Applications**

- Coil Formers
- Jigs and Fixtures
- Low Voltage Insulation
- Pipeline Insulation
- Precision Machined Parts
- Terminal Boards and Tag Strips
- Welding Jigs

### **General Properties**

Property	Unit of measure	Typical Value
Density	g/cm <sup>3</sup>	1.35
Water Absorption	mg	210
Flammability Category <sup>¥</sup>	--	FH1

<sup>¥</sup> Where relevant, the flammability test method is used solely to control and monitor consistency of production. Under no conditions should the results be considered in relation to fire hazards under actual conditions of use.

## Electrical Properties

Property	Unit of measure	Typical Value
IR (24hrs Water Immersed)	G Ω	0.002
IR (Dry)	G Ω	0.002
Electric Strength (Flat Rapid)	MV/m	2
Breakdown Voltage (Edge Step by Step)	kV	12
Tracking Index	V	110

## Mechanical Properties

Property	Unit of measure	Typical Value
Flexural Strength	MPa	180
Impact (Notched CHARPY)	kJ/m <sup>2</sup>	4

## Thermal Properties

Property	Unit of measure	Typical Value
Thermal Rating Continuous	°C	100
Thermal Rating Intermittent	°C	120

Disclaimer: The above values are based upon routine test data and do not form the basis of a supply contract. These products may be used in a diverse range of applications and whilst every effort is made to ensure the

information in this data sheet is accurate, it must be stressed that it is the user's responsibility to ensure suitability for the intended end use.

Source: <https://www.attwater.com/products/b4b/>