

Date Generated: Monday 15th of June 2026**B4PQ Product Data Sheet****BSEN60893-3-4-PFCP201&PFCP207 B4PQ Phenolic Paper
Punching Quality Laminate SRBP****Material Details**

| | |
|------------------------|---|
| Grade: | B4PQ |
| Description: | Phenolic Paper. Punching quality commercial grade |
| Comments: | <p>A cold/warm punching version of B4, available in thickness up to 3mm. Widely used for punching small components, such as fluorescent lamp cap insulators, terminal strips, coil formers and washers.</p> <p>B4PQ can be supplied with black covers upon request.</p> |
| Specifications: | BSEN60893-3-4-PFCP201&PFCP207The closest NEMA equivalent to this specification is NEMA XP |
| Body Colour: | Dark Brown |
| Cover Colour: | Brown |
| Finish: | Satin/Glossy |
| Size: | 1220 x 1220 Thickness Range: 0.8 - 3.0 |

Typical Applications

- Coil Formers
- Insulating Bushes Spacers Sleeves
- Jigs and Fixtures
- Low Voltage Insulation
- Mechanical Applications
- Pipeline Insulation
- Terminal Boards and Tag Strips

General Properties

| Property | Unit of measure | Typical Value |
|------------------------------------|-------------------|---------------|
| Density | g/cm ³ | 1.35 |
| Water Absorption | mg | 66 |
| Flammability Category [¥] | -- | FH1 |

[¥] Where relevant, the flammability test method is used solely to control and monitor consistency of production. Under no conditions should the results be considered in relation to fire hazards under actual conditions of use.

Electrical Properties

| Property | Unit of measure | Typical Value |
|---------------------------------------|-----------------|---------------|
| IR (24hrs Water Immersed) | G Ω | 0.2 |
| IR (Dry) | G Ω | 0.2 |
| Electric Strength (Flat Rapid) | MV/m | 6 |
| Breakdown Voltage (Edge Step by Step) | kV | 40 |
| Tracking Index | V | 110 |

Mechanical Properties

| Property | Unit of measure | Typical Value |
|-------------------------|-------------------|---------------|
| Flexural Strength | MPa | 188 |
| Tensile Strength | MPa | 120 |
| Impact (Notched CHARPY) | kJ/m ² | 4.5 |

Thermal Properties

| Property | Unit of measure | Typical Value |
|---------------------------|-----------------|---------------|
| Thermal Rating Continuous | °C | 100 |

| Property | Unit of measure | Typical Value |
|-----------------------------|-----------------|---------------|
| Thermal Rating Intermittent | °C | 120 |

Disclaimer: The above values are based upon routine test data and do not form the basis of a supply contract. These products may be used in a diverse range of applications and whilst every effort is made to ensure the information in this data sheet is accurate, it must be stressed that it is the user's responsibility to ensure suitability for the intended end use.

Source: <https://www.attwater.com/products/b4pq/>