

Date Generated: Wednesday 11th of February 2026

## G10 Product Data Sheet

# BSEN60893-3-2-EPGC201 G10 Epoxy Glass Laminate SRBG

### Material Details

<b>Grade:</b>	G10
<b>Description:</b>	Epoxy Glass. Commercial epoxy grade
<b>Comments:</b>	General purpose Epoxy glass laminate. Temperature class B (130 deg C), with good mechanical and electrical properties at moderate cost. See also B46.
<b>Specifications:</b>	BSEN60893-3-2-EPGC201 (Which supersedes BS3953 EP3). The closest NEMA equivalent to this specification is NEMA G10
<b>Body Colour:</b>	Green
<b>Cover Colour:</b>	Green
<b>Finish:</b>	Satin/Glossy
<b>Size:</b>	1220 x 1220 Thickness Range: 0.4 - 150.0

### Typical Applications

- Chemical Resistance Components
- Cryogenic Resistance Components
- Electromagnetic Coil Insulation
- High Voltage Insulation
- Insulating Bushes Spacers Sleeves
- Phase Barriers
- Pipeline Insulation
- Precision Machined Parts
- Slot Wedges
- Terminal Boards and Tag Strips
- Transformer Spacers

## General Properties

Property	Unit of measure	Typical Value
Density	g/cm3	2
Water Absorption	mg	8

Where relevant, the flammability test method is used solely to control and monitor consistency of production. Under no conditions should the results be considered in relation to fire hazards under actual conditions of use.

## Electrical Properties

Property	Unit of measure	Typical Value
IR (24hrs Water Immersed)	G Ω	17000
IR (Dry)	G Ω	17000
Electric Strength (Flat Rapid)	kV/mm	15
Breakdown Voltage (Edge Step by Step)	kV	80
Relative Permittivity @ 1 MHz	--	5.2
Dissipation Factor @ 1 MHz	--	0.025
Tracking Index	V	210

## Mechanical Properties

Property	Unit of measure	Typical Value
Flexural Strength	MPa	485
Impact (Notched CHARPY)	kJ/m2	60

## Thermal Properties

Property	Unit of measure	Typical Value
Thermal Rating Continuous	°C	130

Property	Unit of measure	Typical Value
Thermal Rating Intermittent	°C	140

**Disclaimer:** The above values are based upon routine test data and do not form the basis of a supply contract. These products may be used in a diverse range of applications and whilst every effort is made to ensure the information in this data sheet is accurate, it must be stressed that it is the user's responsibility to ensure suitability for the intended end use.

Source: <https://www.attwater.com/products/g10/>