

Date Generated: Monday 23rd of February 2026**G10 rod * Product Data Sheet****G10 Epoxy Glass Moulded Rod SRBG****Material Details**

| | |
|---------------------|--|
| Grade: | G10 rod * |
| Description: | Epoxy Glass Fabric. Epoxy glass fabric moulded rod |
| Comments: | <p>G10 is a moulded rod manufactured from high quality woven E glass fabric which is bonded with an epoxy resin. Rods are available moulded, ground or machined to size required in diameters of up to 100mm. Un-ground rods; Rods supplied as moulded are ideal if you intend to turn finished components. In this condition the rods exhibit some mould lines and can be slightly eccentric. We recommend a selection of rod size that is slightly larger diameter than the required finish size i.e. 10% larger. Whilst the values contained within this datasheet are believed to be indicative of those of the product, batch testing is not carried out. Certification of values may be available subject to individual testing.</p> <p>* Not manufactured by The Attwater Group</p> <p>* Not manufactured by The Attwater Group</p> |
| Body Colour: | Green |
| Finish: | Moulded |
| Size: | Thickness Range: 6-100.0 |

General Properties

| Property | Unit of measure | Typical Value |
|----------|-----------------|---------------|
| Density | g/cm3 | 1.8 |

| Property | Unit of measure | Typical Value |
|------------------|-----------------|---------------|
| Water Absorption | mg | 0.4 |

¥ Where relevant, the flammability test method is used solely to control and monitor consistency of production. Under no conditions should the results be considered in relation to fire hazards under actual conditions of use.

Electrical Properties

| Property | Unit of measure | Typical Value |
|---------------------------|-----------------|---------------|
| IR (24hrs Water Immersed) | G Ω | 100 |

Mechanical Properties

| Property | Unit of measure | Typical Value |
|-------------------|-----------------|---------------|
| Flexural Strength | MPa | 250 min |

Disclaimer: The above values are based upon routine test data and do not form the basis of a supply contract. These products may be used in a diverse range of applications and whilst every effort is made to ensure the information in this data sheet is accurate, it must be stressed that it is the user's responsibility to ensure suitability for the intended end use.

Source: <https://www.attwater.com/products/g10-rod/>