

Date Generated: Wednesday 11th of February 2026

T36 * Product Data Sheet

BSEN61212 EPGC22 T36 Epoxy Glass Tube SRBG

Material Details

| | |
|------------------------|--|
| Grade: | T36 * |
| Description: | Epoxy Glass. A high quality epoxy glass tube which is suitable for use at 155C (Class F). |
| Comments: | A high quality epoxy glass tube which is suitable for use at 155C (Class F). T36 exhibits excellent mechanical and electrical characteristics, low water absorption, high insulation resistance and excellent resistance to axial compression. |
| | * Not manufactured by The Attwater Group. |
| Specifications: | BSEN61212 EPGC22The closest NEMA equivalent to this specification is G11 |
| Body Colour: | Pale Green |
| Finish: | Ground (unless otherwise stated) |
| Size: | 1220mm trimmed (max) Thickness Range: Min ID 9mm, Min wall 1.0mm(Ground) 2.0mm(as produced). |

General Properties

| Property | Unit of measure | Typical Value |
|------------------|-----------------|---------------|
| Density | g/cm3 | 1.9 |
| Water Absorption | mg | 0.2 |

¥ Where relevant, the flammability test method is used solely to control and monitor consistency of production.
 Under no conditions should the results be considered in relation to fire hazards under actual conditions of use.

Electrical Properties

| Property | Unit of measure | Typical Value |
|---------------------------|-----------------|---------------|
| IR (24hrs Water Immersed) | G Ω | 500 |
| IR (Dry) | G Ω | 500 |
| Radial Electric Strength | kV/mm | 11 |

Mechanical Properties

| Property | Unit of measure | Typical Value |
|-------------------|-----------------|---------------|
| Cohesion | MPa | 420 |
| Axial Compressive | MPa | 230 |

Thermal Properties

| Property | Unit of measure | Typical Value |
|---------------------------|-----------------|---------------|
| Thermal Rating Continuous | °C | 155 |

Disclaimer: The above values are based upon routine test data and do not form the basis of a supply contract. These products may be used in a diverse range of applications and whilst every effort is made to ensure the information in this data sheet is accurate, it must be stressed that it is the user's responsibility to ensure suitability for the intended end use.

Source: <https://www.attwater.com/products/t36/>